

# DURO-LAST® 50-MIL MEMBRANE

**ADVANTAGES:**

Duro-Last® 50-Mil (DL50) is an excellent choice for projects requiring a long lasting, energy efficient roofing membrane. The membrane is available in custom-fabricated sections or as roll goods. A complete line of custom-fabricated accessories and parapets are available for use with DL50.

**DESCRIPTION:**

DL50 is composed of PVC film laminated to both sides of a reinforcement fabric (weft-inserted scrim).

**PVC Film** – Proprietary thermoplastic PVC formulation of resins, plasticizers, stabilizers, biocides, flame retardants, and U.V. absorbents.

- PVC film above weft-inserted scrim – 28 mil, nominal

**Weft-Inserted Scrim** – An 18 x 14 polyester fabric construction with weft insertion provides superior tear and puncture resistance. The polyester thread is treated to prevent wicking.

**Total Thickness** – 50 mil, nominal

**Weight** – 0.29 lb/ft<sup>2</sup>

**Colors** – White, tan, gray, dark gray, and terra cotta

**R-Value** – 0.1 R (0.1 ft<sup>2</sup>·°F·hr/Btu)

**AVAILABLE CONFIGURATIONS:**

**Custom-fabricated Sections** – DL50 is available in custom-fabricated sections as listed within the Ordering and Estimating section on the Duro-Last website.



COOL ROOF RATING COUNCIL (CRRC)							
	CRRC ID	Solar Reflectance		Thermal Emittance		Solar Reflective Index (SRI)	
		Initial	3-yr	Initial	3-yr	Initial	3-yr
White	0610-0001a	0.86	0.69	0.89	0.89	109	85
Tan	0610-0005	0.39	0.33	0.89	0.89	43	35
Gray	0610-0004	0.47	0.40	0.89	0.89	54	45
Dark Gray	0610-0006	0.26	0.25	0.87	0.89	25	24
Terra Cotta	0610-0009	0.26	0.24	0.89	0.88	26	23

**LEED-NC & LEED-EB Credits** – Only White DL50 can obtain 1 credit in either U.S. Green Building Council's LEED-NC or LEED-EB programs. In combination with other design criteria the membrane may help attain other credits.

LEED CREDITS	
LEED-NC Credit Category	Duro-Last Attribute
Sustainable Sites Heat Island Reduction	Solar Reflective Index (SRI) = 109
LEED-EB Credit Category	Duro-Last Attribute
Sustainable Sites Heat Island Reduction	Solar Reflective Index (SRI) = 109

ROLL DIMENSIONS <sup>1</sup>				
WIDTH	LENGTH (MAX.)	ROLL AREA	APPROX. WEIGHT	APPROX. COVERAGE <sup>1</sup>
64 inches	100 ft	534 ft <sup>2</sup>	155 lb	483 ft <sup>2</sup>
64 inches	50 ft	267 ft <sup>2</sup>	78 lb	241 ft <sup>2</sup>
32 inches	100 ft	267 ft <sup>2</sup>	78 lb	217 ft <sup>2</sup>
12 inches	100 ft	100 ft <sup>2</sup>	29 lb	N/A
8 inches	100 ft	67 ft <sup>2</sup>	20 lb	N/A

<sup>1</sup> Custom rolls of maximum 64 in. by 240 ft. may be produced upon request.

<sup>2</sup> Assuming 6-inch overlap.

**STORAGE:**

Store rolls lengthwise on pallets. Use tarps to keep rolls dry.

**ENERGY EFFICIENCY:**

White DL50 is an excellent product for complying with California Title 24, LEED® and other energy efficiency programs requiring the use of a highly reflective roof membrane.

**CODES AND STANDARDS:**

Underwriters Laboratories (US & Canada), UL Evaluation Report (ER10128), FM Approvals, Canadian Construction Materials Centre (CCMC 13299-L), State of Florida, Miami-Dade County, Texas Department of Insurance.

**WARRANTY:**

The following warranties are available for projects utilizing DL50. Contact Duro-Last for warranty details.

AVAILABLE WARRANTIES				
<b>SUPREME</b>	15-Year NDL Warranty	20-Year NDL Warranty – 15 Years Consequential Damages And 5 Years Material	20-Year NDL Warranty – 15 Years Consequential Damages And 5 Years Material and Labor	
<b>ULTRA</b>	15-Year NDL Hail Warranty <sup>1</sup>	15-Year NDL Hail & High Wind Warranty <sup>1</sup>	15-Year NDL High Wind Warranty <sup>1</sup>	20-Year NDL High Wind Warranty <sup>1</sup>
<b>BASIC</b>	15-Year NDL Warranty <sup>1</sup>		20-Year NDL Warranty <sup>1</sup>	
<b>RESIDENTIAL</b>	15-Year Residential Material Limited Warranty <sup>1</sup>		20-Year Residential Material Limited Warranty <sup>1</sup>	

<sup>1</sup> Excludes consequential damage coverage.

**MEMBRANE ATTACHMENT:**

**Mechanically Fastened** – DL50 may be mechanically fastened to a variety of roof deck and wall materials. An appropriate slip sheet, insulation or cover board may be required. Refer to the Duro-Last Mechanically Fastened Roofing System Specification for custom-fabricated system requirements. If using roll goods, refer to the Duro-Last Roll Good Mechanically Fastened Roofing System Specification.

**Induction welded** – Induction welding may be used to attach DL50. An appropriate slip sheet, insulation or cover board may be required. Refer to the Duro-Bond® Induction Weld Roofing System Specification for system requirements.

**Adhered** – DL50 may be adhered to a variety of properly prepared roof decks, walls, cover boards and insulations. Refer to the Adhered Roofing System Specification for system requirements.

**PHYSICAL PROPERTIES:**

DL50 has been subjected to the tests required by ASTM D4434 “Standard Specification for Poly (Vinyl Chloride) Sheet Roofing” and has been classified as a Type III, internally reinforced sheet. DL50 also meets or exceeds all ASTM D4434 Type II and Type IV requirements.

The results of each test are listed below. ASTM’s Overall Thickness requirements for the membrane are plus or minus 10% (nominal) of the listed Typical Value.

DL50 PHYSICAL PROPERTIES				
PHYSICAL PROPERTY	TEST METHOD	ASTM D4434 REQUIREMENT	RESULT	TYPICAL VALUE
Overall Thickness	ASTM D751	≥ 0.045 and ≤ 0.055 in. (≥ 45 and ≤ 55 mil)	PASS	0.050 in. (50 mil), nominal
Thickness Over Scrim	ASTM D7635	≥ 0.016 in.	PASS	0.028 in. (28 mil)
Breaking Strength <sup>1</sup>	ASTM D751 Grab Method	≥ 200 lbf./in.	PASS	438 x 390 lbf./in.
Elongation <sup>1</sup>	ASTM D751 Grab Method	≥ 15%	PASS	31% x 31%
Seam Strength	ASTM D751 Grab Method	≥ 328 lbf. (75% of Breaking Strength.)	PASS	417 lbf.
Tear Strength <sup>1</sup>	ASTM D751 Procedure B	≥ 45 lbf.	PASS	132 x 163 lbf.
Low Temp. Bend	ASTM D2136	Must pass at -40° F	PASS	PASS
Heat Aging	ASTM D3045	Conditioned for 56 days in oven maintained at 176° F.	PASS	PASS
Accelerated Aging	ASTM G155	10,000 hours total test time. Irradiance level of 0.35 W/m <sup>2</sup> -340nm. Cycle: 102 minutes light, 18 minutes light + H <sub>2</sub> O spray, 63±2.5° C black panel, 30±5% RH	PASS	PASS
Dimensional Stability <sup>1</sup>	ASTM D1204	Conditioned for 6 hours in oven maintained at 176° F. Allowable change: ≤ 0.5%	PASS	-0.30% x -0.45%
Water Absorption	ASTM D570	Immersed in water at 158° F for 168 hours. Allowable weight change: ≤ 3%	PASS	1.7%
Static Puncture	ASTM D5602	≥ 33 lbf.	PASS	PASS
Dynamic Puncture	ASTM D5635	≥ 14.7 ft-lbf. (20 J)	PASS	PASS

<sup>1</sup> Typical values are shown for both machine and cross machine directions. The machine direction results are listed first.

ADDITIONAL TESTS		
Fungi Resistance	ASTM G21	No Sustained Growth or Discoloration
Moisture Vapor Transmission	ASTM E96, Proc. B, Method A	< 0.35 U.S. perms



Duro-Last, the “World’s Best Roof”, and Duro-Bond are trademarks in the Amrize portfolio. All other trademarks are property of their respective owners.